Machining Parameters Optimization for the Surface Roughness through Taguchi Analysis

Ravi Shankar Raman[1], Sandeep Pratap Singh[2], Tarun Sharma[3] & Sudhir Kumar[4]

[1]Associate Professor, ABES Engineering College, Ghaziabad, U.P., India.
[2 3 4] Students of Mechanical Engineering, ABES Engineering College, Ghaziabad, U.P., India.
ravi.raman21@gmail.com[1], sandeepthakur8534@gmail.com[2]

Abstract: *Assembling production is bit by bit changing to green production because of the expanding production cost. production cost and the impact on the earth can diminish by decreasing tool wear underway. Hence, it turns into a vital issue for the manufacturing production. This examination explores the optimal machining parameters (speed, cutting depth and feed rate) and the connection between's control parameters The practicability of the ideal parameters was in addition checked through many manufacturing process yet confronting is best trial among them. It is discovered that the proposed strategy in the examination is material to widespread applications. An orthogonal array was set-up and used to break down the impact of the control parameters(speed, cutting depth and feed rate) on surface roughness . The outcome shows that the Taguchi strategy can decide the best combination of machining parameters and it can give the ideal machining response conditions which are the most minimal surface roughness.*

Keywords: *Taguchi Analysis, Facing Operation, Orthogonal Matrix, ANOVA*

1. INTRODUCTION

The Taguchi technique is a measurable strategy used to improve the nature of the items and it is developed by Genuchi Taguchi. At the point when the quantity of process parameters expands countless exploratory work must be done and to take care of this issue, the Taguchi strategy utilizes an extraordinary symmetrical exhibit with just few investigations to examine the whole parameter space. The advantage of this method is the saving of efforts in conducting experiments, experimental time, the cost and discovering significant factors in less time period. For the structure of a top-notch item the Taguchi's hearty plan strategy is an amazing asset. The Taguchi technique helps as a quality device to improve the work effectively. For the most part quality is estimated by the deviation of value attributes from its objective worth. In this way, the goal is to make a plan which is obtuse toward every single wild factor and their potential blends. The Taguchi strategy helps as a quality instrument to streamline a presentation, improving quality and lessening the expense. The nature of configuration can be improved by improving quality and efficiency in. The different exercises of organization worried about quality remember for nature of item arranging, item structure and procedure plan. S/N proportion is a significant instrument utilized in robust structure. S/N proportion estimates quality with accentuation on variety. OA obliges many structure factors all the while so it is a significant instrument too.

2. LITERATURE ABOUT PROCESS DEVELOPMENT

Numerous techniques have been created to optimize the manufacturing processes. Some are discussed below.

2.1 One Factor at a Time

As the name suggested we could consider only one factor at a time for experiment, thus it is quite expensive and very time-consuming analysis. Since only one factor can be taken at a time, therefore Interactions between factors are not possible during the process. Generally, it is optimizing the whole process by running an experiment at one particular condition and repeating the experiment by changing one factor to another factor individually.

2.2 Design of Experiments

This measurable methodology give prescient information on a complex, multi-variable procedure with barely any preliminaries. There are the significant ways to deal with DOE.

2.2.1 Full Factorial Analysis

Full factorial analysis makes exploratory focuses utilizing all the potential blends of the degrees of the variables in each total preliminary or replication of the tests. The trial configuration focuses in a full factorial structure are the vertices of a hypercube in the n-dimensional plan space characterized by the base and the extreme estimations of every one of the components. These test focuses are likewise called factorial focuses. For three variables having three degrees of each factor, thinking about full factorial structure, all out 3^3 (27) quantities of analyses must be done. On the off chance, that there are n imitates of complete examinations, at that point there will be n times of the single replication analyses to be directed.

2.2.2 Taguchi Method:

The Taguchi strategy utilizes an exceptional symmetrical cluster with just few investigations to contemplate the whole parameter space Taguchi proposed an extraordinarily planned methodwhich is the utilization of symmetrical exhibit for the investigation of whole parameter space with lesser number of tests to be led. To quantify the exhibition attributes, Taguchi suggests the utilization of the misfortune capacity to gauge the presentation qualities that are going astray from the ideal objective worth. The estimation of this misfortune work is additionally changed into (S/N (signal-to-commotion)) ratio.Generally; there are three classes of the presentation attributes to break down the S/N proportion.

- Analysis of Nominal to better
- Analysis of Larger to better
- Analysis of Smaller to better

3. STEPS FOR TAGUCHI METHOD

The step for taguchi method is as follows

1. Identification of the fundamental capacity and the impacts of that work.
2. Determine the uncontrollable factors and testing conditions with quality attributes.
3. Identification of the target work which is to be advanced.
4. Determine the possible control factors and their associate levels.
5. Select an Orthogonal matrix.
6. Perform the Matrix experiment.
7. Assessment of the information and foresee the ideal of control factor levels and the presentation of its.
8. Run the confirmation test.

4. IDENTIFICATION OF CONTROL AND UNCONTROL FACTORS

As per the means that are associated with Taguchi's Method, a progression of experiments are to be directed. Here, facing operation on mild steel cylindrical components using a CNC lathe machine has been completed as a case study analysis. The technique is given underneath.

4.1 Identification of the Controllable and Uncontrollable factors, testing conditions and quality attributes

Quality Measured: Surface roughness
Work piece material: Mild Steel
Cutting Tool Type: Tungsten Carbide Tipped tool
Working Machine: CNC machine
Testing Equipment: Surface Roughness Testing Machine

The "Variables" that influence facing operation on a CNC appeared in table 1

Table 1. Identification of Controllable and Uncontrollable Factors

Controllable factors	Uncontrollable factors
Cutting Speed Parameters	Vibration
Depth of cut	Machine condition
Feed rate	Crude material variety
Nose radius	Temperature
Coolant	Operator Skill

4.2 Identification of the target work

Target Function: Expression for Smaller-the-Better , S/N Ratio for this capacity:

$$\eta = -10 \log_{10}\left(\frac{1}{n}\sum_{i=1}^{n} y^2{}_i\right)$$

In the above expression n is the Sample Size and y is the Surface Roughness.

4.3 Identification of the control factors and levels

To identify the various control factors and levels, a brain storming session was organised and found the control factors and levels as shown in table:2

Table: Controllable factors and their levels

FACTORS	LEVELS		
	1	2	3
Cutting speed(rpm)	2200	1000	3400
Depth of cut (mm)	0.4	0.3	0.5
Feed rate(mm/min)	130	115	145

4.3 Selection of an Appropriate Orthogonal Array and Construction of the Matrix

DOF: 8 for all three factors, i.e (2x4=8)
One for Mean Value
Thus, Total DOF= 8+1=9
Therefore based on the total DOF, select suitable orthogonal array for experiment is L_9.

Table 3: Orthogonal Matrix L9 for experiment

Experiment No.	Control Factors		
	Cutting speed	Depth of cut	Feed rate
1	1	1	1
2	1	2	2
3	1	3	3
4	2	1	3
5	2	2	1
6	2	3	2
7	3	1	2
8	3	2	3
9	3	3	1

4.4: Conduct the Matrix experiment

Every one of the over 9 examinations were directed multiple times implies (27 trials) to represent the varieties that may happen because of the clamor factors. The surface roughness (Ra) was estimated utilizing the surface unpleasantness testing machine.

The deliberate estimations of surface roughness acquired from various trials appeared in table: 4

Table 4: Conduct the Matrix experiment

Experiment No.	Control Factors		
	V(in rpm)	t(in mm)	F(in mm/min)
1	2200	0.4	130
2	2200	0.3	115
3	2200	0.5	145
4	1000	0.4	145
5	1000	0.3	130
6	1000	0.5	115
7	3400	0.4	115
8	3400	0.3	145
9	3400	0.5	130

Table 5: Measured values of surface roughness

Experiment No.	Surface Roughness (Ra in µm)			
	1	2	3	Mean Value
1	2.4	2.48	2.82	2.57
2	2.55	3.65	2.69	2.96
3	2.48	2.87	4.15	3.17
4	2.29	3.43	4.84	3.52
5	2.61	3.72	4.42	3.58
6	4.81	4.3	4.4	4.51
7	2.09	2.54	3.84	2.82
8	4.45	2.55	3.15	3.39
9	3.95	2.24	3.34	3.18

4.5 Assessment of the information and foresee the ideal control factor levels and the presentation of its

The following are the experimental results of the work carried out.

4.5.1: Experimental Details

The S/N ratios of all the experiments were calculated and tabulated in table: 6

Table 6 : Signal to Noise Ratio's

Experiment No.	S/N Ratio (in dB)
1	-8.20919
2	-9.55224
3	-10.227
4	-11.2963
5	-11.2696
6	-13.0811
7	-9.3053
8	-10.8192
9	-10.2497

The S/N proportion for the individual control factors are determined and their values are shown in the table 7

Table 7: Signal to Noise ratio for individual control factors

Level	Speed		Feed		Depth of Cut	
	Sum	Average S/N ratio	Sum (Sfj)	Average S/N ratio	Sum	Average S/N ratio
1	3.869	-11.88	3.31	-10.55	3.22	-10.366
2	2.899	-9.329	2.97	-9.604	3.484	-10.703
3	3.128	-10.13	3.616	-11.19	3.191	-10.267



Figure 1: Main Effect Plot for Mean Values of the Control Factors



Figure 2: Main Effect Plot for Signal to Noise Ratios of the Control Factors

The Proposed objective function "Smaller-the-Better" was used for calculating the Surface Roughness as shown.

$$\eta = -10\log_{10}\left(\frac{1}{n}\sum_{i=1}^{n} y^2_i\right)$$

The factor levels comparing to the most noteworthy S/N proportion were picked to streamline the condition. From these straight charts obviously the ideal estimations of the components and their levels are as given in table 8.

Table 8: Values of Surface Roughness

Parameter	Optimum Value
Speed	1000
Feed Rate	0.3
Depth of cut	145

4.5.2 Run the Confirmation Test

Table 9: Confirmation Test Values of Surface Roughness

Experiment No.	Surface Roughness, Ra (μm)
1	2.02
2	2.06
3	2.04
4	2.02
5	2.04
Mean Value	**2.036**

5. SIGNIFICANCE OF ANNOVA ANALYSIS

The ANOVA study performed to research the factual importance of the procedure parameters influencing the reaction (apparatus life). This is accomplished by isolating the all out inconstancy of the S/N proportions, which is estimated by the entirety of the squared deviations from the complete mean of the S/N proportion, into commitments by every one of the procedure parameters and the blunder.

Table 10: Analysis of Variance:

Source	DOF	Sum of Square (SS)	Adj MS Verror	F-Value	P-Value	Remark
Cutting Speed	2	1.68560	0.84280	42.07	**0.023**	**Significance**
Depth of Cut	2	3.39527	1.69763	84.74	**0.012**	**Significance**
Feed Rate	2	3.43327	1.71663	85.69	**0.016**	**Significance**
Error	2	0.04007	0.02003			
Total	8	8.55420				

At 95% confidence

The fundamental property of ANOVA is that the all out entireties of the squares (absolute variety) is equivalent to the aggregate of the SS (wholes of the squares of the deviations) of all the condition parameters and the blunder parts, i.e., including the varieties of every factor. The Calculated P-Values of all the factors is less than 0.5 so all the factors have significance impact on the surface roughness phenomena.

6. CONCLUSION

This paper shows the utilization of the parameter plan (Taguchi technique) in the improvement of surface roughness properties. The accompanying ends can be drawn dependent on the above trial after effects of this examination:

- It is discovered that the parameter plan of the Taguchi technique gives a straight forward, precise, and effective philosophy for improving the procedure parameters and hence improve the surface roughness properties.

- Taguchi's Method can be performed with less number of experiments when contrasted with that of full factorial investigation so it is less expensive analysis.

- It is discovered that the parameter plan of the Taguchi strategy gives a straight forward, precise, and productive philosophy for advancing the procedure parameters.

7. References

[1.] Taguchi G, Konishi S ,Taguchi Methods, orthogonal arrays and linear graphs, tools for quality American supplier institute, American Supplier Institute; 1987.

[2.] Ravi Shankar Raman , DMAIC Approach for Road Wellbeing: A Case Study", International Journal of Engineering & Technology(UAE), Volume 7, Issue 4.5, Page 8-11,August 2018.

[3.] Ernest Doebelin, Engineering Experimentation, Tata MCGRAW HILL Publication

[4.] Domnita Fratilia, Cristian Caizar, Application of Taguchi method to selection of optimal lubrication and cutting conditions in face milling of AlMg3, Journal of Cleaner Production 19 (2011) 640-645.

[5.] W.T. Foster, Basic Taguchi design of experiments, National Association of Industrial Technology Conference, Pittsburgh, PA, 2000.

[6] Pathan, L.K.; Bhivsane, S.V. Experimental Analysis and Investigation of Machining Parameters in Finish Hard Turning of AISI 4340 Steel